

# BLANCO LINER SAICA

## White Top Testliner C

CEPI code: 72

Exclusively available in 120 g/m<sup>2</sup>

It is the perfect paper for economic white packaging. Sized.



### target characteristics

TEST	STANDARD	UNIT	BLANCO LINER SAICA
Nominal basis weight	ISO 536	lb/msf	<b>24,6</b>
Nominal moisture index	ISO 287	%	8
SCT, CD	ISO 9895	lbf/in	9,1
RCT, CD*1	ISO 12192	lbf/in	*
Bursting strength	EN ISO 2758	psi	26
COBB-60	EN ISO 535	g/m <sup>2</sup>	35
Brightness	ISO 2470-1	%	67
b*	ISO 5631-2		-3
Roughness (Bendtsen)	ISO 8791-2	ml/min	400

### guaranteed characteristics

TEST	STANDARD	UNIT	BLANCO LINER SAICA
Nominal basis weight			<b>24,6</b>
Mean basis weight	ISO 536	lb/msf	nominal +/- 3%
Nominal moisture index			8
Mean moisture index	ISO 287	%	nominal -1+0,5
SCT, CD	ISO 9895	lbf/in	7,4
RCT, CD*1	ISO 12192	lbf/in	*
Bursting strength	EN ISO 2758	psi	23
COBB-60	EN ISO 535	g/m <sup>2</sup>	50
Brightness min-max	ISO 2470-1	%	64-70
Plybond minimum	TAPPI T 833	ft lbf/in <sup>2</sup>	85,7
Production centre			

\*RCT,CD is not a valid test for weights less than 28,9 lb/msf

\*1 RCT,DT values are calculated from a correlation with SCT-DT



100% Recycled and responsibly manufactured paper

Valid from December 2020