

# BLANCO LINER SAICA

## White Top Testliner C

CEPI code: 72

Exclusively available in 120 g/m<sup>2</sup>

It is the perfect paper for economic white packaging. Sized.



### target characteristics

TEST	STANDARD	UNIT	BLANCO LINER SAICA
Nominal basis weight	ISO 536	g/m <sup>2</sup>	<b>120</b>
Nominal moisture index	ISO 287	%	8
Bursting strength	EN ISO 2758	kPa	180
		kPa.m <sup>2</sup> /g	1,5
SCT, CD	ISO 9895	kN/m	1,6
		kN.m/kg	13
COBB-60	EN ISO 535	g/m <sup>2</sup>	35
Brightness	ISO 2470 -1	%	67
b*	ISO 5631-2		-3
Roughness (Bendtsen)	ISO 8791-2	ml/min	400

### guaranteed characteristics

TEST	STANDARD	UNIT	BLANCO LINER SAICA
Nominal basis weight	ISO 536	g/m <sup>2</sup>	<b>120</b>
Mean basis weight		nominal ± 3%	
Nominal moisture index	ISO 287	%	8
Mean moisture index		nominal -1+0,5	
Bursting strength	EN ISO 2758	kPa	156
		kPa.m <sup>2</sup> /g	1,3
SCT, CD	ISO 9895	kN/m	1,3
		kN.m/kg	11
COBB-60 maximum	EN ISO 535	g/m <sup>2</sup>	50
Brightness min/max.	ISO 2470-1	%	64-70
Plybond minimum	TAPPI T 833	J/m <sup>2</sup>	180
Production centre			

The index guaranteed values refer to the nominal basis weight



100% Recycled and responsibly manufactured paper

Valid from September 2019