AQUA

# BLS | BLANCO LINER SAICA

## White Top Testliner C

**CEPI code: 72**

### Characteristics:

- Available exclusively in 110 and 120 g/m².
- Sized paper.
- Suitable for food contact*.

### Applications:

- Optimal printing quality.
- Sustainable packaging.
- Light industry.
- Food and beverage.

* For contact conditions and/or special instructions, see our Declaration of Conformity.

100% recycled and recyclable papers

SAICA

# BLS | BLANCO LINER SAICA

## White Top Testliner C

* For contact conditions and/or special instructions, see our Declaration of Conformity.

## target characteristics

| TEST | STANDARD | UNIT | BLANCO LINER SAICA | |
|---|---|---|---|---|
| Nominal basis weight | ISO 536<br>ISO 18522 | g/m² | **110** | **120** |
| Nominal moisture index | On-line | % | 8 | 8 |
| Bursting strength | ISO 2758<br>ISO 18522 | kPa | 165 | 180 |
| | | kPa.m²/g | 1,5 | 1,5 |
| SCT, CD | ISO 9895<br>ISO 18522 | kN/m | 1,4 | 1,6 |
| | | kN.m/kg | 13 | 13 |
| COBB-60 | ISO 535 | g/m² | 35 | 35 |
| Brightness | ISO 2470-1 | % | 68 | 68 |
| b* | ISO 5631-2 | | -3 | -3 |
| Roughness (Bendtsen) | ISO 8791-2<br>ISO 18522 | ml/min | 400 | 400 |

## guaranteed characteristics

| TEST | STANDARD | UNIT | BLANCO LINER SAICA | |
|---|---|---|---|---|
| Nominal basis weight | ISO 536<br>ISO 18522 | g/m² | **110** | **120** |
| Mean basis weight | | | nominal ± 3% | |
| Nominal moisture index | On-line | % | 8 | 8 |
| Mean moisture index | | | nominal -1+0,5 | |
| Bursting strength | ISO 2758<br>ISO 18522 | kPa | 143 | 156 |
| | | kPa.m²/g | 1,3 | 1,3 |
| SCT, CD | ISO 9895<br>ISO 18522 | kN/m | 1,2 | 1,3 |
| | | kN.m/kg | 11 | 11 |
| COBB-60 maximum | ISO 535 | g/m² | 50 | 50 |
| Brightness min/max. | ISO 2470-1 | % | 65-71 | |
| Plybond minimum | TAPPI T 833 | J/m² | 180 | 180 |
| Production centre | | | SP | SP |

The index guaranteed values refer to the nominal basis weight.

Access the complete and always updated file.

Valid from May 2025.