

DPS | DUOPLUS SAICA

High performance fluting / Testliner 1



* For contact conditions and/or special instructions, see our Declaration of Conformity.

target characteristics

TEST	STANDARD	UNIT	DUOPLUS		
Nominal basis weight	ISO 536	lb/msf	19,5	21,5	23,6
Nominal moisture index	On-line	%	8	9	9
CMT 30/50, MD	EN ISO 7263	lbf	36,4	40,2	51,7
CMT 0, MD ²	EN ISO 7263	lbf	49,1	54,2	70,4
SCT, CD	ISO 9895	lbf/in	10,9	12,6	14,3
RCT, CD ¹	ISO 12192	lbf/6in	-	-	-
Bursting strength	EN ISO 2758	psi	36	41	47
COBB-60	EN ISO 535	g/m ²	35	35	35
COBB-1800 ³	EN ISO 535	g/m ²	-	-	-

guaranteed characteristics

TEST	STANDARD	UNIT	DUOPLUS		
Nominal basis weight	ISO 536	lb/msf	19,5	21,5	23,6
Mean basis weight					
Nominal moisture index	On-line	%	8	9	9
Mean moisture index					
CMT 30/50, MD	EN ISO 7263	lbf	32,1	35,5	44,1
CMT 0, MD ²	EN ISO 7263	lbf	42,9	47,4	59,3
SCT, CD	ISO 9895	lbf/in	9,7	10,9	13,1
RCT, CD ¹	ISO 12192	lbf/6in	-	-	-
Bursting strength	EN ISO 2758	psi	32	37	42
COBB-60	EN ISO 535	g/m ²	50	50	50
COBB-1800 ³	EN ISO 535	g/m ²	-	-	-
Production centre			UK	UK	UK

The index guaranteed values refer to the nominal basis weight.

¹ RCT, CD is not a valid test for weights less than 24,8 lb/msf. Values are calculated from a correlation with SCT, CD.

² CMT 0, MD values are calculated from a correlation with CMT 30/50, MD.

³ COBB-1800 guaranteed only for paper produced at Saica Paper France.

CEPI code: 58



100% recycled and recyclable papers

Valid from June 2023.