

DPS | DUOPLUS SAICA

High performance fluting / Testliner 1



* For contact conditions and/or special instructions, see our Declaration of Conformity.

target characteristics

TEST	STANDARD	UNIT	DUOPLUS		
Nominal basis weight	ISO 536	g/m ²	95	105	115
Nominal moisture index	On-line	%	8	9	9
SCT, CD	ISO 9895	kN/m	1,9	2,2	2,5
		kN.m/kg	20	20,5	22
CMT 30/50, MD	EN ISO 7263	N	162	179	230
		N.m ² /g	1,7	1,7	2
Bursting strength	EN ISO 2758	kPa	247	284	322
		kPa.m ² /g	2,6	2,7	2,8
COBB-60	EN ISO 535	g/m ²	35	35	35
COBB-1800*	EN ISO 535	g/m ²	-	-	-

guaranteed characteristics

TEST	STANDARD	UNIT	DUOPLUS		
Nominal basis weight	ISO 536	g/m ²	95	105	115
Mean basis weight		nominal ± 3%			
Nominal moisture index	On-line	%	8	9	9
Mean moisture index			nominal -1+0,5		
SCT, CD	ISO 9895	kN/m	1,7	1,9	2,3
		kN.m/kg	18	18,5	20
CMT 30/50, MD	EN ISO 7263	N	143	158	196
		N.m ² /g	1,5	1,5	1,7
Bursting strength	EN ISO 2758	kPa	219	252	288
		kPa.m ² /g	2,3	2,4	2,5
COBB-60 maximum	EN ISO 535	g/m ²	50	50	50
COBB-1800 maximum*	EN ISO 535	g/m ²	-	-	-
Production centre			UK	UK	UK

The index guaranteed values refer to the nominal basis weight.

* Cobb -1800 guaranteed only for paper produced at Saica Paper France.

CEPI code: 58



100% recycled and recyclable papers

Valid from June 2023.