

Infinite lithos

White Top Testliner Coated

CEPI code: 79

target characteristics

TEST	STANDARD	UNIT	INFINITE LITHOS		
Nominal basis weight	ISO 536	g/m ²	150	165	180
Nominal moisture index	ISO 287	%	6	6	6
Bursting strength	EN ISO 2758	kPa	330	363	396
		kPa.m ² /g	2,2	2,2	2,2
SCT, CD	ISO 9895	kN/m	2,9	3,1	3,3
		kN.m/kg	19	19	18,5
COBB-60	EN ISO 535	g/m ²	35	35	35
COBB-60 reverse					
COBB-1800	EN ISO 535	g/m ²	130	130	130
Brightness	ISO 2470-1	%	83	83	83
Roughness (Parker)	ISO 8791-4	PPS	1,7	1,9	2,1
Plybond	TAPPI T 833	J/m ²	350	350	330

guaranteed characteristics

TEST	STANDARD	UNIT	INFINITE LITHOS		
Nominal basis weight	ISO 536	g/m ²	150	165	180
Mean basis weight					
Nominal moisture index	ISO 287	%	6	6	6
Mean moisture index					
Bursting strength	EN ISO 2758	kPa	285	314	342
		kPa.m ² /g	1,9	1,9	1,9
SCT, CD	ISO 9895	kN/m	2,6	2,8	3,1
		kN.m/kg	17	17	17
COBB-60 max	EN ISO 535	g/m ²	50	50	50
COBB-60 max reverse					
COBB-1800 max	EN ISO 535	g/m ²	150	150	150
Brightness min/max.	ISO 2470-1	%		80-86	
Roughness (Parker)	ISO 8791-4	PPS	2,5	2,5	2,7
Plybond minimum	TAPPI T 833	J/m ²	300	300	260
Production centre			SP	SP	SP

The index guaranteed values refer to the nominal basis weight

White Top Testliner Coated for printing sheets and litho-laminating. Paper with high level of whiteness to obtain maximum printing quality.

Available in different grammages that allow reductions in the final weight of packaging whilst maintaining its technical characteristics. Alternative to GD2.



100% Recycled and responsibly manufactured paper

Valid from September 2019