


Infinite[∞]coated

White Top Testliner Coated

CEPI code: 77

Coated White Top Testliner for high print quality (with driers).

Optimum smoothness and even whiteness thanks to the double coating. IC is an alternative to the best coated Testliners on the market.



target characteristics

TEST	STANDARD	UNIT	INFINITE COATED					
Nominal basis weight	ISO 536	lb/msf	25,6	27,7	30,7	33,8	36,9	39,9
Nominal moisture index	ISO 287	%	8	8	8	8	8	8
SCT, CD	ISO 9895	lbf/in	13,1	14,9	16,6	17,7	18,9	20,6
RCT, CD*1	ISO 12192	lbf/in	*	*	*	*	59,3	67,8
Bursting strength	EN ISO 2758	psi	40	43	48	53	57	62
COBB-60	EN ISO 535	g/m ²	35	35	35	35	35	35
COBB-1800	EN ISO 535	g/m ²	*	130	130	130	130	130
Brightness	ISO 2470-1	%	83	83	83	83	83	83
Roughness (Parker)	SO 8791-4	µm	1,7	1,7	1,9	1,9	2,1	2,1
Plybond	TAPPI T 833	ft lbf/in ²	166,5	166,5	166,5	166,5	166,5	166,5

guaranteed characteristics

TEST	STANDARD	UNIT	INFINITE COATED					
Nominal basis weight	ISO 536	lb/msf	25,6	27,7	30,7	33,8	36,9	39,9
Mean basis weight			nominal +- 3%					
Nominal moisture index	ISO 287	%	8	8	8	8	8	8
Mean moisture index			nominal -1+0,5					
SCT, CD	ISO 9895	lbf/in	11,4	13,1	14,9	16	17,7	18,9
RCT, CD*1	ISO 12192	lbf/in	*	*	*	*	53,7	59,3
Bursting strength	EN ISO 2758	psi	35	37	41	46	50	54
COBB-60	EN ISO 535	g/m ²	50	50	50	50	50	50
COBB-1800	EN ISO 535	g/m ²	*	150	150	150	150	150
Brightness min-max	ISO 2470-1	%	80-86	80-86	80-86	80-86	80-86	80-86
Roughness (Parker)	ISO 8791-4	µm	2,3	2,3	2,5	2,5	2,7	2,7
Plybond minimum	TAPPI T 833	ft lbf/in ²	142,8	142,8	142,8	142,8	119,0	100
Production centre			SP	SP	SP	SP	SP	SP



Valid from December 2020

*RCT,CD is not a valid test for weights less than 35 lb/msf
 *1 RCT,DT values are calculated from a correlation with SCT-DT