


Infinite coated

White Top Testliner Coated

CEPI code: 77

Coated White Top Testliner for high print quality (with driers).

Optimum smoothness and even whiteness thanks to the double coating. IC is an alternative to the best coated Testliners on the market.



target characteristics

TEST	STANDARD	UNIT	INFINITE COATED				
Nominal basis weight	ISO 536	g/m ²	125	135	150	165	180
Nominal moisture index	ISO 287	%	8	8	8	8	8
Bursting strength	EN ISO 2758	kPa	275	297	330	363	396
		kPa.m ² /g	2,2	2,2	2,2	2,2	2,2
SCT, CD	ISO 9895	kN/m	2,3	2,6	2,9	3,1	3,3
		kN.m/kg	18	19	19	19	18,5
COBB-60	EN ISO 535	g/m ²	35	35	35	35	35
COBB-1800	EN ISO 535	g/m ²	-	130	130	130	130
Brightness	ISO 2470-1	%	83	83	83	83	83
Roughness (Parker)	ISO 8791-4	PPS	1,7	1,7	1,9	1,9	2,1
Plybond	TAPPI T 833	J/m ²	350	350	350	350	330

guaranteed characteristics

TEST	STANDARD	UNIT	INFINITE COATED				
Nominal basis weight	ISO 536	g/m ²	125	135	150	165	180
Mean basis weight			nominal ± 3%				
Nominal moisture index	ISO 287	%	8	8	8	8	8
Mean moisture index			nominal -1+0,5				
Bursting strength	EN ISO 2758	kPa	238	257	285	314	342
		kPa.m ² /g	1,9	1,9	1,9	1,9	1,9
SCT, CD	ISO 9895	kN/m	2	2,3	2,6	2,8	3,1
		kN.m/kg	16	17	17	17	17
COBB-60 max	EN ISO 535	g/m ²	50	50	50	50	50
COBB-1800 max	EN ISO 535	g/m ²	-	150	150	150	150
Brightness min/max.	ISO 2470-1	%	80-86				
Roughness (Parker)	ISO 8791-4	PPS	2,3	2,3	2,5	2,5	2,7
Plybond minimum	TAPPI T 833	J/m ²	300	300	300	300	260
Production centre			ESP	SP	SP	SP	SP

The index guaranteed values refer to the nominal basis weight



100% Recycled and responsibly manufactured paper

Valid from June 2020