

IL | INTERLINER

Testliner 4 / fluting 2



* For contact conditions and/or special instructions, see our Declaration of Conformity.

target characteristics

TEST	STANDARD	UNIT	INTERLINER	
Nominal basis weight	ISO 536	lb/msf	15,4	20,5
Nominal moisture index	On-line	%	8	8
SCT, CD	ISO 9895	lbf/in	5,7	8
RCT, CD ¹	ISO 12192	lbf/6in	-	-
Bursting strength	EN ISO 2758	psi	17	26

guaranteed characteristics

TEST	STANDARD	UNIT	INTERLINER	
Nominal basis weight	ISO 536	lb/msf	15,4	20,5
Mean basis weight				
Nominal moisture index	On-line	%	8	8
Mean moisture index				
SCT, CD	ISO 9895	lbf/in	4,6	6,9
RCT, CD ¹	ISO 12192	lbf/in	-	-
Bursting strength	EN ISO 2758	psi	15	23
Production centre			SP	SP

The index guaranteed values refer to the nominal basis weight.

¹ RCT, CD is not a valid test for weights less than 24,8 lb/msf. Values are calculated from a correlation with SCT, CD.

CEPI code: 57



100% recycled and recyclable papers

Valid from June 2023.