


INTERLINER

testliner 4 / fluting 2

CEPI code: 50

Light weight, double use paper from 75 g/m²

It gives great economy with excellent runnability.
The perfect paper for the most cost-effective packaging in the market.



target characteristics

TEST	STANDARD	UNIT	INTERLINER	
Nominal basis weight	ISO 536	g/m ²	75	100
Nominal moisture index	ISO 287	%	8	8
Bursting strength	EN ISO 2758	kPa	120	180
		kPa.m ² /g	1,6	1,8
SCT, CD	ISO 9895	kN/m	1	1,4
		kN.m/kg	12,7	13,7

guaranteed characteristics

TEST	STANDARD	UNIT	INTERLINER	
Nominal basis weight	ISO 536	g/m ²	75	100
Mean basis weight		nominal ± 2%		
Nominal moisture index	ISO 287	%	8	8
Mean moisture index		nominal -1+0,5		
Bursting strength	EN ISO 2758	kPa	105	160
		kPa.m ² /g	1,4	1,6
SCT, CD	ISO 9895	kN/m	0,8	1,2
		kN.m/kg	10,7	11,5
Production centre			SP	SP

The index guaranteed values refer to the nominal basis weight



100% Recycled
and responsibly
manufactured paper

Valid from September 2019