

# IL | INTERLINER

## Testliner 4 / fluting 2



\* For contact conditions and/or special instructions, see our Declaration of Conformity.

### target characteristics

TEST	STANDARD	UNIT	INTERLINER	
Nominal basis weight	ISO 536	g/m <sup>2</sup>	75	100
Nominal moisture index	On-line	%	8	8
Bursting strength	EN ISO-2758	kPa	120	180
		kPa.m <sup>2</sup> /g	1,6	1,8
SCT, CD	ISO 9895	kN/m	1	1,4
		kN.m/kg	12,7	13,7

### guaranteed characteristics

TEST	STANDARD	UNIT	INTERLINER	
Nominal basis weight	ISO 536	g/m <sup>2</sup>	75	100
Mean basis weight				nominal ± 2%
Nominal moisture index	On-line	%	8	8
Mean moisture index				
Bursting strength	EN ISO-2758	kPa	105	160
		kPa.m <sup>2</sup> /g	1,4	1,6
SCT, CD	ISO 9895	kN/m	0,8	1,2
		kN.m/kg	10,7	11,5
Production centre			SP	SP

The index guaranteed values refer to the nominal basis weight.

CEPI code: 57



100% recycled and recyclable papers

Valid from June 2023.