


Infinite innova

White Top Testliner Light Coated

CEPI code: 78

White testliner with the ideal level of coating to enhance printing (with or without driers).

Innovative paper with an even spotless whiteness. Oriented towards applications demanding high performance in industry as well as agriculture. Versatile quality suitable for a wide range of Flexo printers.



target characteristics

TEST	STANDARD	UNIT	INFINITE INNOVA				
Nominal basis weight	ISO 536	lb/msf	20,5	23,6	24,6	27,7	33,8
Nominal moisture index	ISO 287	%	8	8	8	8	8
SCT, CD	ISO 9895	lbf/in	10,3	12,6	13,1	14,9	17,7
RCT, CD*1	ISO 12192	lbf/6in	*	*	*	*	*
Bursting strength	EN ISO 2758	psi	33	42	44	49	60
COBB-60	EN ISO 535	g/m ²	35	35	35	35	*
COBB-1800	EN ISO 535	g/m ²	*	*	*	*	130
Brightness	ISO 2470-1	%	76	76	76	76	76
Roughness (Bendtsen)	ISO 8791-2	ml/min	200	200	200	220	310
Plybond	TAPPI T 833	ft lbf/in ²	190,3	190,3	190,3	190,3	157

guaranteed characteristics

TEST	STANDARD	UNIT	INFINITE INNOVA				
Nominal basis weight	ISO 536	lb/msf	20,5	23,6	24,6	27,7	33,8
Mean basis weight			nominal +/- 3%				
Nominal moisture index	ISO 287	%	8	8	8	8	8
Mean moisture index			nominal -1+0,5				
SCT, CD	ISO 9895	lbf/in	9,1	11,4	11,4	13,1	16
RCT, CD*1	ISO 12192	lbf/6in	*	*	*	*	*
Bursting strength	EN ISO 2758	psi	29	37	38	43	53
COBB-60	EN ISO 535	g/m ²	50	50	50	50	*
COBB-1800	EN ISO 535	g/m ²	*	*	*	*	150
Brightness min-max	ISO 2470-1	%	73-79	73-79	73-79	73-79	73-79
Roughness (Bendtsen)	ISO 8791-2	ml/min	400	400	400	450	450
Plybond minimum	TAPPI T 833	ft lbf/in ²	166,5	166,5	166,5	166,5	123,7
Production centre			SP	SP	SP	SP	SP

*RCT,CD is not a valid test for weights less than 35 lb/msf

*1 RCT,DT values are calculated from a correlation with SCT-DT



Valid from December 2020