

IN | Infinite innova

White Top Testliner Light Coated



* For contact conditions and/or special instructions, see our Declaration of Conformity.

target characteristics

TEST	STANDARD	UNIT	INFINITE INNOVA				
Nominal basis weight	ISO 536	g/m ²	100	115	120	135	165
Nominal moisture index	On-line	%	7,5	7,5	7,5	7,5	7,5
Bursting strength	EN ISO-2758	kPa	230	288	300	338	413
		kPa.m ² /g	2,3	2,5	2,5	2,5	2,5
SCT, CD	ISO 9895	kN/m	1,8	2,2	2,3	2,6	3,1
		kN.m/kg	18	19	19	19	19
COBB-60	EN ISO 535	g/m ²	40	40	40	40	-
COBB-1800	EN ISO 535	g/m ²	-	-	-	-	130
Brightness	ISO 2470-1	%	76	76	76	76	76
Roughness (Bendtsen)	ISO 8791-2	ml/min	290	290	290	310	310
Plybond	TAPPI T 833	J/m ²	400	400	400	400	330

guaranteed characteristics

TEST	STANDARD	UNIT	INFINITE INNOVA				
Nominal basis weight	ISO 536	g/m ²	100	115	120	135	165
Mean basis weight		nominal ± 3%					
Nominal moisture index	On-line	%	7,5	7,5	7,5	7,5	7,5
Mean moisture index		nominal -1+0,5					
Bursting strength	EN ISO-2758	kPa	200	253	264	297	363
		kPa.m ² /g	2	2,2	2,2	2,2	2,2
SCT, CD	ISO 9895	kN/m	1,6	2	2	2,3	2,8
		kN.m/kg	16	17	17	17	17
COBB-60 maximum	EN ISO 535	g/m ²	50	50	50	50	-
COBB-1800 maximum	EN ISO 535	g/m ²	-	-	-	-	150
Brightness min/max	ISO 2470-1	%	73-79				
Roughness (Bendtsen)	ISO 8791-2	ml/min	400	400	400	450	450
Plybond minimum	TAPPI T 833	J/m ²	350	350	350	350	260
Production centre			SP	SP	SP	SP	SP

The index guaranteed values refer to the nominal basis weight.

CEPI code: 79



100% recycled and recyclable papers

Valid from June 2023.