

# 10 | **Infinite**∞one

## White Top Testliner Light Coated

CEPI code: 73

### Characteristics:

- White semi-coated paper with absorption capacity.
- Available in 19,5 and 22,5 lb/msf.
- Suitable for food contact\*.

### Applications:

- Optimized for flexographic printing.
- White applications for the industrial sector.
- Versatility. Food and beverages.

\* For contact conditions and/or special instructions, see our Declaration of Conformity.



100% recycled  
and recyclable  
papers

# 10 | Infiniteone

## White Top Testliner Light Coated



\* For contact conditions and/or special instructions, see our Declaration of Conformity.

### target characteristics

TEST	STANDARD	UNIT	INFINITE ONE	
Nominal basis weight	ISO 536	lb/msf	19,5	22,5
Nominal moisture index	On-line	%		7,5
SCT, CD	ISO 9895	lbf/in	8,6	11
RCT, CD *1	ISO 12192	lbf/6in		*
Bursting strength	EN ISO 2758	psi	26	34
COBB-60	EN ISO 535	g/m <sup>2</sup>		40
COBB-1800	EN ISO 535	g/m <sup>2</sup>		*
Brightness	ISO 2470-1	%		64
Roughness (Bendtsen)	ISO 8791-2	ml/min		290
Plybond	TAPPI T 833	ft lbf/in <sup>2</sup>		119,0

### guaranteed characteristics

TEST	STANDARD	UNIT	INFINITE ONE	
Nominal basis weight	ISO 536	lb/msf	19,5	22,5
Mean basis weight				nominal +- 3%
Nominal moisture index	On-line	%		7,5
Mean moisture index				nominal -1+0,5
SCT, CD	ISO 9895	lbf/in	7,4	9,7
RCT, CD *1	ISO 12192	lbf/6in		*
Bursting strength	EN ISO 2758	psi	23	30
COBB-60	EN ISO 535	g/m <sup>2</sup>		50
COBB-1800	EN ISO 535	g/m <sup>2</sup>		*
Brightness min-max	ISO 2470-1	%		61-67
Roughness (Bendtsen)	ISO 8791-2	ml/min		400
Plybond minimum	TAPPI T 833	ft lbf/in <sup>2</sup>		95,2
Production centre			SP	SP

\*RCT,CD is not a valid test for weights less than 35 lb/msf

\*1 RCT,DT values are calculated from a correlation with SCT-DT



Access the complete and always updated file.

Valid from May 2025.