AQUA

10 | Infinite one

White Top Testliner Light Coated

CEPI code: 73

Characteristics:

- White semi-coated paper with absorption capacity.
- Available in 95 g/m² y 110 g/m².
- Suitable for food contact*.

Applications:

- Optimized for flexographic printing.
- White applications for the industrial sector.
- Versatility. Food and beverages.

* For contact conditions and/or special instructions, see our Declaration of Conformity.

100% recycled and recyclable papers

SAICA

I0 | Infiniteone

White Top Testliner Light Coated

* For contact conditions and/or special instructions, see our Declaration of Conformity.

target characteristics

TEST	STANDARD	UNIT	INFINITE ONE	
Nominal basis weight	ISO 536 ISO 18522	g/m²	**95**	**110**
Nominal moisture index	On-line	%	7,5	7,5
Bursting strength	ISO 2758 ISO 18522	kPa	181	231
		kPa.m²/g	1,9	2,1
SCT, CD	ISO 9895 ISO 18522	kN/m	1,5	1,9
		kN.m/kg	16	17
COBB-60	ISO 535	g/m²	40	40
Brightness	ISO 2470-1	%	64	64
Roughness (Bendtsen)	ISO 8791-2 ISO 18522	ml/min	290	290
Plybond	TAPPI T 833	J/m²	250	250

guaranteed characteristics

TEST	STANDARD	UNIT	INFINITE ONE	
Nominal basis weight	ISO 536 ISO 18522	g/m²	**95**	**110**
Mean basis weight			nominal ± 3%	
Nominal moisture index	On-line	%	7,5	7,5
Mean moisture index			nominal -1+0,5	
Bursting strength	ISO 2758 ISO 18522	kPa	162	209
		kPa.m²/g	1,7	1,9
SCT, CD	ISO 9895 ISO 18522	kN/m	1,3	1,7
		kN.m/kg	14	15
COBB-60 maximum	ISO 535	g/m²	50	50
Brightness min/max	ISO 2470-1	%	61-67	
Roughness (Bendtsen)	ISO 8791-2 ISO 18522	ml/min	400	400
Plybond minimum	TAPPI T 833	J/m²	200	200
Production centre			SP	SP

The index guaranteed values refer to the nominal basis weight.

Access the complete and always updated file.

Valid from October 2025.