

# SAIKRAFT BLANCO

## White Top Testliner A

CEPI code: 70

Excellent appearance and smoothness.  
For high compression strength performances  
and a high quality range of printing. Sized.



### target characteristics

TEST	STANDARD	UNIT	SAIKRAFT BLANCO		
Nominal basis weight	ISO 536	lb/msf	<b>25,6</b>	<b>28,7</b>	<b>34,8</b>
Nominal moisture index	ISO 287	%	8	8	8
SCT, CD	ISO 9895	lbf/in	13,7	15,4	18,3
RCT, CD*1	ISO 12192	lbf/6in	*	*	56,5
Bursting strength	EN ISO 2758	psi	47	53	62
COBB-60	EN ISO 535	g/m <sup>2</sup>	25	25	25
COBB-1800	EN ISO 535	g/m <sup>2</sup>	100	100	100
Brightness	ISO 2470-1	%	76	76	76
b*	ISO 5631-2		-9	-9	-9
Roughness (Bendtsen)	ISO 8791-2	ml/min	300	325	350

### guaranteed characteristics

TEST	STANDARD	UNIT	SAIKRAFT BLANCO		
Nominal basis weight			<b>25,6</b>	<b>28,7</b>	<b>34,8</b>
Mean basis weight	ISO 536	lb/msf		nominal +- 3%	
Nominal moisture index			8	8	8
Mean moisture index	ISO 287	%		nominal -1+0,5	
SCT, CD	ISO 9895	lbf/in	12	13,7	16,6
RCT, CD*1	ISO 12192	lbf/6in	*	*	48,1
Bursting strength	EN ISO 2758	psi	42	47	54
COBB-60	EN ISO 535	g/m <sup>2</sup>	50	50	50
COBB-1800	EN ISO 535	g/m <sup>2</sup>	150	150	150
Brightness min-max	ISO 2470-1	%	73-79	73-79	73-79
Plybond minimum	TAPPI T 833	ft lbf/in <sup>2</sup>	166,5	166,5	142,8
Production centre			SP	SP	SP

\*RCT,CD is not a valid test for weights less than 28,9 lb/msf

\*1 RCT,DT values are calculated from a correlation with SCT-DT



100% Recycled  
and responsibly  
manufactured paper

Valid from December 2020