

# SKB | SAIKRAFT BLANCO

## White Top Testliner A



\* For contact conditions and/or special instructions, see our Declaration of Conformity.

### target characteristics

TEST	STANDARD	UNIT	SAIKRAFT BLANCO			
Nominal basis weight	ISO 536	lb/msf	25,6	27,7	28,7	34,8
Nominal moisture index	On-line	%	8	8	8	8
SCT, CD	ISO 9895	lbf/in	13,7	14,9	15,4	18,3
RCT, CD <sup>1</sup>	ISO 12192	lbf/6in	-	-	-	56,5
Bursting strength	EN ISO 2758	psi	47	51	53	62
COBB-60	EN ISO 535	g/m <sup>2</sup>	25	25	25	25
COBB-1800	EN ISO 535	g/m <sup>2</sup>	100	100	100	100
Brightness	ISO 2470-1	%	76	76	76	76
b*	ISO 5631-2		-9	-9	-9	-9
Roughness (Bendtsen)	ISO 8791-2	ml/min	300	315	325	350

### guaranteed characteristics

TEST	STANDARD	UNIT	SAIKRAFT BLANCO			
Nominal basis weight	ISO 536	lb/msf	25,6	27,7	28,7	34,8
Mean basis weight						
Nominal moisture index	On-line	%	8	8	8	8
Mean moisture index						
SCT, CD	ISO 9895	lbf/in	12	13,1	13,7	16,6
RCT, CD <sup>1</sup>	ISO 12192	lbf/6in	-	-	-	48,1
Bursting strength	EN ISO 2758	psi	42	45	47	54
COBB-60	EN ISO 535	g/m <sup>2</sup>	50	50	50	50
COBB-1800	EN ISO 535	g/m <sup>2</sup>	150	150	150	150
Brightness min-max	ISO 2470-1	%	73-79	73-79	73-79	73-79
Plybond minimum	TAPPI T 833	ft lbf/in <sup>2</sup>	166,5	166,5	166,5	142,8
Production centre			SP	SP	SP	SP

The index guaranteed values refer to the nominal basis weight.

<sup>1</sup> RCT, CD is not a valid test for weights less than 28,9 lb/msf. Values are calculated from a correlation with SCT, CD.

CEPI code: 70



100% recycled and recyclable papers

Valid from June 2023.