

SKB | SAIKRAFT BLANCO

White Top Testliner A



* For contact conditions and/or special instructions, see our Declaration of Conformity.

target characteristics

| TEST | STANDARD | UNIT | SAIKRAFT BLANCO | | |
|------------------------|-------------|------------------|-----------------|------|------|
| Nominal basis weight | ISO 536 | lb/msf | 25,6 | 28,7 | 34,8 |
| Nominal moisture index | On-line | % | 8 | 8 | 8 |
| SCT, CD | ISO 9895 | lbf/in | 13,7 | 15,4 | 18,3 |
| RCT, CD ¹ | ISO 12192 | lbf/6in | - | - | 56,5 |
| Bursting strength | EN ISO 2758 | psi | 47 | 53 | 62 |
| COBB-60 | EN ISO 535 | g/m ² | 25 | 25 | 25 |
| COBB-1800 | EN ISO 535 | g/m ² | 100 | 100 | 100 |
| Brightness | ISO 2470-1 | % | 76 | 76 | 76 |
| b* | ISO 5631-2 | | -9 | -9 | -9 |
| Roughness (Bendtsen) | ISO 8791-2 | ml/min | 300 | 325 | 350 |

guaranteed characteristics

| TEST | STANDARD | UNIT | SAIKRAFT BLANCO | | |
|------------------------|-------------|------------------------|-----------------|-------|-------|
| Nominal basis weight | ISO 536 | lb/msf | 25,6 | 28,7 | 34,8 |
| Mean basis weight | | | | | |
| Nominal moisture index | On-line | % | 8 | 8 | 8 |
| Mean moisture index | | | | | |
| SCT, CD | ISO 9895 | lbf/in | 12 | 13,7 | 16,6 |
| RCT, CD ¹ | ISO 12192 | lbf/6in | - | - | 48,1 |
| Bursting strength | EN ISO 2758 | psi | 42 | 47 | 54 |
| COBB-60 | EN ISO 535 | g/m ² | 50 | 50 | 50 |
| COBB-1800 | EN ISO 535 | g/m ² | 150 | 150 | 150 |
| Brightness min-max | ISO 2470-1 | % | 73-79 | 73-79 | 73-79 |
| Plybond minimum | TAPPI T 833 | ft lbf/in ² | 166,5 | 166,5 | 142,8 |
| Production centre | | | SP | SP | SP |

The index guaranteed values refer to the nominal basis weight.

¹ RCT, CD is not a valid test for weights less than 28,9 lb/msf. Values are calculated from a correlation with SCT, CD.

CEPI code: 70



100% recycled and recyclable papers

Valid from June 2023.