

# SKB | SAIKRAFT BLANCO

## White Top Testliner A



\* For contact conditions and/or special instructions, see our Declaration of Conformity.

### target characteristics

TEST	STANDARD	UNIT	SAIKRAFT BLANCO			
Nominal basis weight	ISO 536	g/m <sup>2</sup>	125	135	140	170
Nominal moisture index	On-line	%	8	8	8	8
Bursting strength	EN ISO-2758	kPa	325	351	364	425
		kPa.m <sup>2</sup> /g	2,6	2,6	2,6	2,5
SCT, CD	ISO 9895	kN/m	2,4	2,6	2,7	3,2
		kN.m/kg	19	19	19	19
COBB-60	EN ISO 535	g/m <sup>2</sup>	25	25	25	25
COBB-1800	EN ISO 535	g/m <sup>2</sup>	100	100	100	100
Brightness	ISO 2470-1	%	76	76	76	76
b*	ISO 5631-2		-9	-9	-9	-9
Roughness (Bendtsen)	ISO 8791-2	ml/min	300	315	325	350

### guaranteed characteristics

TEST	STANDARD	UNIT	SAIKRAFT BLANCO			
Nominal basis weight	ISO 536	g/m <sup>2</sup>	125	135	140	170
Mean basis weight		nominal ± 3%				
Nominal moisture index	On-line	%	8	8	8	8
Mean moisture index		nominal -1+0,5				
Bursting strength	EN ISO-2758	kPa	288	311	322	374
		kPa.m <sup>2</sup> /g	2,3	2,3	2,3	2,2
SCT, CD	ISO 9895	kN/m	2,1	2,3	2,4	2,9
		kN.m/kg	17	17	17	17
COBB-60 maximum	EN ISO 535	g/m <sup>2</sup>	50	50	50	50
COBB-1800 maximum	EN ISO 535	g/m <sup>2</sup>	150	150	150	150
Brightness min/max.	ISO 2470-1	%	73-79			
Plybond minimum	TAPPI T 833	J/m <sup>2</sup>	350	350	350	300
Production centre			SP	SP	SP	SP

The index guaranteed values refer to the nominal basis weight.

CEPI code: 70



100% recycled and recyclable papers

Valid from June 2023.