

# SKB | SAIKRAFT BLANCO

## White Top Testliner A

CEPI code: 70

### Characteristics:

- Excellent whiteness and smoothness.
- High degree of sizing.
- Suitable for food contact\*.

### Applications:

- High printing quality.
- Sustainable packaging.
- Export fruit and vegetable market.
- Heavy industry.
- Climatic chambers, frozen goods.
- Food and beverage.
- Trays.

\* For contact conditions and/or special instructions, see our Declaration of Conformity.



100% recycled  
and recyclable  
papers

# SKB | SAIKRAFT BLANCO

## White Top Testliner A



\* For contact conditions and/or special instructions, see our Declaration of Conformity.

### target characteristics

TEST	STANDARD	UNIT	SAIKRAFT BLANCO		
Nominal basis weight	ISO 536	g/m <sup>2</sup>	125	140	170
Nominal moisture index	On-line	%	8	8	8
Bursting strength	EN ISO-2758	kPa	325	364	425
		kPa.m <sup>2</sup> /g	2,6	2,6	2,5
SCT, CD	ISO 9895	kN/m	2,4	2,7	3,2
		kN.m/kg	19	19	19
COBB-60	EN ISO 535	g/m <sup>2</sup>	25	25	25
COBB-1800	EN ISO 535	g/m <sup>2</sup>	100	100	100
Brightness	ISO 2470-1	%	76	76	76
b*	ISO 5631-2		-9	-9	-9
Roughness (Bendtsen)	ISO 8791-2	ml/min	300	325	350

### guaranteed characteristics

TEST	STANDARD	UNIT	SAIKRAFT BLANCO		
Nominal basis weight	ISO 536	g/m <sup>2</sup>	125	140	170
Mean basis weight		nominal ± 3%			
Nominal moisture index	On-line	%	8	8	8
Mean moisture index		nominal -1+0,5			
Bursting strength	EN ISO-2758	kPa	288	322	374
		kPa.m <sup>2</sup> /g	2,3	2,3	2,2
SCT, CD	ISO 9895	kN/m	2,1	2,4	2,9
		kN.m/kg	17	17	17
COBB-60 maximum	EN ISO 535	g/m <sup>2</sup>	50	50	50
COBB-1800 maximum	EN ISO 535	g/m <sup>2</sup>	150	150	150
Brightness min/max.	ISO 2470-1	%		73-79	
Plybond minimum	TAPPI T 833	J/m <sup>2</sup>	350	350	300
Production centre			SP	SP	SP

The index guaranteed values refer to the nominal basis weight.



Access the complete and always updated file.

Valid from May 2025.