

# SKB | SAIKRAFT BLANCO

## White Top Testliner A



\* For contact conditions and/or special instructions, see our Declaration of Conformity.

### target characteristics

| TEST                   | STANDARD    | UNIT                  | SAIKRAFT BLANCO |     |     |
|------------------------|-------------|-----------------------|-----------------|-----|-----|
| Nominal basis weight   | ISO 536     | g/m <sup>2</sup>      | 125             | 140 | 170 |
| Nominal moisture index | On-line     | %                     | 8               | 8   | 8   |
| Bursting strength      | EN ISO-2758 | kPa                   | 325             | 364 | 425 |
|                        |             | kPa.m <sup>2</sup> /g | 2,6             | 2,6 | 2,5 |
| SCT, CD                | ISO 9895    | kN/m                  | 2,4             | 2,7 | 3,2 |
|                        |             | kN.m/kg               | 19              | 19  | 19  |
| COBB-60                | EN ISO 535  | g/m <sup>2</sup>      | 25              | 25  | 25  |
| COBB-1800              | EN ISO 535  | g/m <sup>2</sup>      | 100             | 100 | 100 |
| Brightness             | ISO 2470-1  | %                     | 76              | 76  | 76  |
| b*                     | ISO 5631-2  |                       | -9              | -9  | -9  |
| Roughness (Bendtsen)   | ISO 8791-2  | ml/min                | 300             | 325 | 350 |

### guaranteed characteristics

| TEST                   | STANDARD    | UNIT                  | SAIKRAFT BLANCO |       |     |
|------------------------|-------------|-----------------------|-----------------|-------|-----|
| Nominal basis weight   | ISO 536     | g/m <sup>2</sup>      | 125             | 140   | 170 |
| Mean basis weight      |             |                       | nominal ± 3%    |       |     |
| Nominal moisture index | On-line     | %                     | 8               | 8     | 8   |
| Mean moisture index    |             |                       | nominal -1+0,5  |       |     |
| Bursting strength      | EN ISO-2758 | kPa                   | 288             | 322   | 374 |
|                        |             | kPa.m <sup>2</sup> /g | 2,3             | 2,3   | 2,2 |
| SCT, CD                | ISO 9895    | kN/m                  | 2,1             | 2,4   | 2,9 |
|                        |             | kN.m/kg               | 17              | 17    | 17  |
| COBB-60 maximum        | EN ISO 535  | g/m <sup>2</sup>      | 50              | 50    | 50  |
| COBB-1800 maximum      | EN ISO 535  | g/m <sup>2</sup>      | 150             | 150   | 150 |
| Brightness min/max.    | ISO 2470-1  | %                     |                 | 73-79 |     |
| Plybond minimum        | TAPPI T 833 | J/m <sup>2</sup>      | 350             | 350   | 300 |
| Production centre      |             |                       | SP              | SP    | SP  |

The index guaranteed values refer to the nominal basis weight.