AQUA

SKB | SAIKRAFT BLANCO

White Top Testliner A

CEPI code: 70

Characteristics:

- Excellent whiteness and smoothness.
- High degree of sizing.
- Suitable for food contact*.

Applications:

- High printing quality.
- Sustainable packaging.
- Export fruit and vegetable market.
- Heavy industry.
- Climatic chambers, frozen goods.
- Food and beverage.
- Trays.

* For contact conditions and/or special instructions, see our Declaration of Conformity.

100% recycled
and recyclable
papers

SAICA

SKB | SAIKRAFT BLANCO

White Top Testliner A

* For contact conditions and/or special instructions, see our Declaration of Conformity.

target characteristics

TEST	STANDARD	UNIT	SAIKRAFT BLANCO		
Nominal basis weight	ISO 536 ISO 18522	g/m²	**125**	**140**	**170**
Nominal moisture index	On-line	%	8	8	8
Bursting strength	ISO 2758 ISO 18522	kPa	325	364	425
		kPa.m²/g	2,6	2,6	2,5
SCT, CD	ISO 9895 ISO 18522	kN/m	2,4	2,7	3,2
		kN.m/kg	19	19	19
COBB-60	ISO 535	g/m²	25	25	25
COBB-1800	ISO 535	g/m²	100	100	100
Brightness	ISO 2470-1	%	76	76	76
b*	ISO 5631-2		-9	-9	-9
Roughness (Bendtsen)	ISO 8791-2 ISO 18522	ml/min	300	325	350

guaranteed characteristics

TEST	STANDARD	UNIT	SAIKRAFT BLANCO		
Nominal basis weight	ISO 536 ISO 18522	g/m²	**125**	**140**	**170**
Mean basis weight				nominal ± 3%	
Nominal moisture index	On-line	%	8	8	8
Mean moisture index				nominal -1+0,5	
Bursting strength	ISO 2758 ISO 18522	kPa	288	322	374
		kPa.m²/g	2,3	2,3	2,2
SCT, CD	ISO 9895 ISO 18522	kN/m	2,1	2,4	2,9
		kN.m/kg	17	17	17
COBB-60 maximum	ISO 535	g/m²	50	50	50
COBB-1800 maximum	ISO 535	g/m²	150	150	150
Brightness min/max.	ISO 2470-1	%		73-79	
Plybond minimum	TAPPI T 833	J/m²	350	350	300
Production centre			SP	SP	SP

The index guaranteed values refer to the nominal basis weight.

Access the complete and always updated file.

Valid from May 2025.