

TBS | TEST BLANCO SAICA

White Top Testliner B



* For contact conditions and/or special instructions, see our Declaration of Conformity.

target characteristics

TEST	STANDARD	UNIT	TEST BLANCO SAICA	
Nominal basis weight	ISO 536	lb/msf	25,6	27,7
Nominal moisture index	On-line	%	8	8
SCT, CD	ISO 9895	lbf/in	11,4	12,6
RCT, CD ¹	ISO 12192	lbf/6in	-	-
Bursting	EN ISO 2758	psi	36	39
COBB-60	EN ISO 535	g/m ²	35	35
Brightness	ISO 2470-1	%	72	72
b*	ISO 5631-2		-6	-6
Roughness (Bendtsen)	ISO 8791-2	ml/min	300	350

guaranteed characteristics

TEST	STANDARD	UNIT	TEST BLANCO SAICA	
Nominal basis weight	ISO 536	lb/msf	25,6	27,7
Mean basis weight			nominal ± 3%	
Nominal moisture index	On-line	%	8	8
Mean moisture index			nominal -1+0,5	
SCT, CD	ISO 9895	lbf/in	9,7	10,3
RCT, CD ¹	ISO 12192	lbf/6in	-	-
Bursting strength	EN ISO 2758	psi	33	35
COBB-60	EN ISO 535	g/m ²	50	50
Brightness min-max	ISO 2470-1	%	69-75	69-75
Plybond minimum	TAPPI T 833	ft lbf/in ²	130,9	130,9
Production centre			SP	SP

The index guaranteed values refer to the nominal basis weight.

¹ RCT, CD is not a valid test for weights less than 28,9 lb/msf. Values are calculated from a correlation with SCT, CD.

CEPI code: 71



100% recycled and recyclable papers

Valid from June 2023.