

TEST BLANCO SAICA

White Top Testliner B

CEPI code: 71

Optimal degree of whiteness and smoothness.

Made for application which require a high compression strength performance and print quality. Sized.



target characteristics

TEST	STANDARD	UNIT	TEST BLANCO SAICA	
Nominal basis weight	ISO 536	g/m ²	125	135
Nominal moisture index	ISO 287	%	8	8
Bursting strength	EN ISO 2758	kPa	250	270
		kPa.m ² /g	2	2
SCT, CD	ISO 9895	kN/m	2	2.2
		kN.m/kg	16	16
COBB-60	EN ISO 535	g/m ²	35	35
Brightness	ISO 2470-1	%	72	72
b*	ISO 5631-2		-6	-6
Roughness (Bendtsen)	ISO 8791-2	ml/min	300	350

guaranteed characteristics

TEST	STANDARD	UNIT	TEST BLANCO SAICA	
Nominal basis weight	ISO 536	g/m ²	125	135
Mean basis weight		nominal ± 3%		
Nominal moisture index	ISO 287	%	8	8
Mean moisture index		nominal -1+0,5		
Bursting strength	EN ISO 2758	kPa	225	243
		kPa.m ² /g	1,8	1,8
SCT, CD	ISO 9895	kN/m	1,7	1,8
		kN.m/kg	13,5	13,5
COBB-60 maximum	EN ISO 535	g/m ²	50	50
Brightness min/max.	ISO 2470-1	%	69-75	
Plybond minimum	TAPPI T 833	J/m ²	275	
Production centre			SP	SP

The index guaranteed values refer to the nominal basis weight



100% Recycled and responsibly manufactured paper

Valid from September 2019