

SAIKRAFT BLANCO

white liner A

CEPI code: 70



Excellent appearance and smoothness for high compression strength performances and a high quality range of printing. Sized.



100% Recycled and responsibly manufactured paper

target characteristics

TEST	STANDARD	UNIT	SAIKRAFT BLANCO		
Nominal basis weight	ISO 536	g/m ²	125	140	170
Nominal moisture index	ISO 287	%	8	8	8
Bursting strength	EN ISO 2758	kPa	325	364	425
		kPa.m ² /g	2,6	2,6	2,5
SCT, CD	ISO 9895	kN/m	2,4	2,7	3,2
		kN.m/kg	19	19	19
COBB-60	EN ISO 535	g/m ²	25	25	25
COBB-1800	EN ISO 535	g/m ²	100	100	100
Brightness	ISO 2470	%	76	76	76
b*			-9	-9	-9
Roughness (Bendtsen)	ISO 8791-2	ml/min	300	325	350

guaranteed characteristics

TEST	STANDARD	UNIT	SAIKRAFT BLANCO		
Nominal basis weight	ISO 536	g/m ²	125	140	170
Mean basis weight			nominal ± 3%		
Nominal moisture index	ISO 287	%	8	8	8
Mean moisture index			nominal -1+0,5		
Bursting strength	EN ISO 2758	kPa	288	322	374
		kPa.m ² /g	2,3	2,3	2,2
SCT, CD	ISO 9895	kN/m	2,1	2,4	2,9
		kN.m/kg	17	17	17
COBB-60 maximum	EN ISO 535	g/m ²	50	50	50
COBB-1800 maximum	EN ISO 535	g/m ²	150	150	150
Brightness min/max.	ISO 2470	%	73-79		
Plybond minimum	TAPPI T 833	J/m ²	350	350	300
Production centre			SP	SP	SP

The index guaranteed values refer to the nominal basis weight

Valid from January 2018