


# TEST BLANCO SAICA

white liner B

CEPI code: 71



Optimal degree of whiteness and smoothness.

Made for application which require a high compression strength performance and print quality. Sized..



100% Recycled and responsibly manufactured paper

## target characteristics

TEST	STANDARD	UNIT	TEST BLANCO SAICA	
Nominal basis weight	ISO 536	g/m <sup>2</sup>	<b>125</b>	<b>135</b>
Nominal moisture index	ISO 287	%	8	8
Bursting strength	EN ISO 2758	kPa	250	270
		kPa.m <sup>2</sup> /g	2	2
SCT, CD	ISO 9895	kN/m	2	2,2
		kN.m/kg	16	16
COBB-60	EN ISO 535	g/m <sup>2</sup>	35	35
Brightness	ISO 2470	%	72	72
b*			-6	-6
Roughness (Bendtsen)	ISO 8791-2	ml/min	300	350

## guaranteed characteristics

TEST	STANDARD	UNIT	TEST BLANCO SAICA	
Nominal basis weight	ISO 536	g/m <sup>2</sup>	<b>125</b>	<b>135</b>
Mean basis weight		nominal ± 3%		
Nominal moisture index	ISO 287	%	8	8
Mean moisture index		nominal -1+0,5		
Bursting strength	EN ISO 2758	kPa	225	243
		kPa.m <sup>2</sup> /g	1,8	1,8
SCT, CD	ISO 9895	kN/m	1,7	1,8
		kN.m/kg	13,5	13,5
COBB-60 maximum	EN ISO 535	g/m <sup>2</sup>	50	50
Brightness min/max.	ISO 2470	%	69-75	
Plybond minimum	TAPPI T 833	J/m <sup>2</sup>	275	
Production centre			SP	SP

The index guaranteed values refer to the nominal basis weight

Valid from January 2018