

LEYDLINER 2

test liner 2

CEPI code: 20



We produce a large grammage range, from 125 to 210 g/m², sized, allowing use of this product in numerous corrugated applications and in general packaging markets.



The characteristics of this product are much higher than the industry standards and it is adapted to optimisation: principally, the reduction of grammage and the number of board grades.



100% Recycled and responsibly manufactured paper

target characteristics

TEST	STANDARD	UNIT	LEYDLINER 2				
Nominal basis weight	ISO 536	g/m ²	125	140	170	200	210
Nominal moisture index	ISO 287	%	8,5	8,5	8,5	8,5	8,5
Bursting strength	EN ISO 2758	kPa	345	395	470	550	570
		kPa.m ² /g	2,8	2,8	2,8	2,8	2,7
SCT, CD	ISO 9895	kN/m	2,31	2,63	3,30	3,90	4,10
		kN.m/kg	18	19	19	20	20
Cobb-60	EN ISO 535	g/m ²	35	35	35	35	35

guaranteed characteristics

TEST	STANDARD	UNIT	LEYDLINER 2				
Nominal basis weight	ISO 536	g/m ²	125	140	170	200	210
Variation		← nominal ± 3% → ← ± 4% →					
Nominal moisture index	ISO 287	%	8,5	8,5	8,5	8,5	8,5
Variation		nominal ± 1,5%					
Bursting strength	EN ISO 2758	kPa	325	365	450	515	530
		kPa.m ² /g	2,6	2,6	2,6	2,6	2,5
SCT, CD	ISO 9895	kN/m	2,20	2,40	3,10	3,70	3,90
		kN.m/kg	18	17	18	19	19
Cobb-60 maximum	EN ISO 535	g/m ²	40	40	40	40	40
Cobb-1800 maximum	EN ISO 535	g/m ²	150	150	150	150	150

The index guaranteed values refer to the nominal basis weight.

Valid from June 2018