

Infinite innova

White Top Testliner Light Coated

CEPI code: 78



White testliner with the ideal level of coating to enhance printing (with or without driers).

Innovative paper with an even spotless whiteness.

Oriented towards applications demanding high performance in industry as well as agriculture.

Versatile quality suitable for a wide range of Flexo printers.



100% Recycled and responsibly manufactured paper

target characteristics

TEST	STANDARD	UNIT	INFINITE INNOVA			
Nominal basis weight	ISO 536	g/m ²	110	120	135	165
Nominal moisture index	ISO 287	%	8	8	8	8
Bursting strength	EN ISO 2758	kPa	275	300	338	413
		kPa.m ² /g	2,5	2,5	2,5	2,5
SCT, DT	ISO 9895	kN/m	2,1	2,3	2,6	3,1
		kN.m/kg	19	19	19	19
COBB-60	EN ISO 535	g/m ²	35	35	35	-
COBB-1800	EN ISO 535	g/m ²	-	-	-	130
Brightness	ISO 2470	%	76	76	76	76
Roughness (Bendtsen)	ISO 8791-2	ml/min	200	200	220	310
Plybond	TAPPI T 833	J/m ²	400	400	400	330

guaranteed characteristics

TEST	STANDARD	UNIT	INFINITE INNOVA			
Nominal basis weight	ISO 536	g/m ²	110	120	135	165
Mean basis weight		nominal ± 3%				
Nominal moisture index	ISO 287	%	8	8	8	8
Mean moisture index		nominal -1+0,5				
Bursting strength	EN ISO 2758	kPa	242	264	297	363
		kPa.m ² /g	2,2	2,2	2,2	2,2
SCT, DT	ISO 9895	kN/m	1,9	2	2,3	2,8
		kN.m/kg	17	17	17	17
COBB-60 max	EN ISO 535	g/m ²	50	50	50	-
COBB-1800 max	EN ISO 535	g/m ²	-	-	-	150
Brightness min/max.	ISO 2470	%	73-79			
Roughness (Bendtsen)	ISO 8791-2	ml/min	400	400	450	450
Plybond minimum	TAPPI T 833	J/m ²	350	350	350	260
Production centre			SP	SP	SP	SP

The index guaranteed values refer to the nominal basis weight

Valid from July 2018