

SAIKRAFT

kraft liner type

CEPI code: 10

Brown sized liner (T1) with higher compression strength.

Made for applications with high compression strength and high performance requirements for industry and agriculture .



target characteristics

TEST	STANDARD	UNIT	SAIKRAFT							
			115	125	135	140	170	200	220	250
Nominal basis weight	ISO 536	g/m ²	115	125	135	140	170	200	220	250
Nominal moisture index	ISO 287	%	9,5	9,5	9,5	9,5	9,5	9,5	9,5	9,5
Bursting strength	EN ISO 2758	kPa	345	375	405	420	510	600	660	750
		kPa.m ² /g	3	3	3	3	3	3	3	3
SCT, CD	ISO 9895	kN/m	2,5	2,8	3	3,1	3,7	4,4	4,8	5,5
		kN.m/kg	22	22	22	22	22	22	22	22
COBB-60	EN ISO 535	g/m ²	30	30	30	30	-	-	-	-
COBB-1800	EN ISO 535	g/m ²	-	-	-	-	125	125	125	125

guaranteed characteristics

TEST	STANDARD	UNIT	SAIKRAFT							
			115	125	135	140	170	200	220	250
Nominal basis weight	ISO 536	g/m ²	115	125	135	140	170	200	220	250
Mean basis weight			nominal ± 3%							
Nominal moisture index	ISO 287	%	9,5	9,5	9,5	9,5	9,5	9,5	9,5	9,5
Mean moisture index			nominal -1+0,5							
Bursting strength	EN ISO 2758	kPa	299	325	351	364	442	520	572	650
		kPa.m ² /g	2,6	2,6	2,6	2,6	2,6	2,6	2,6	2,6
SCT, CD	ISO 9895	kN/m	2,2	2,4	2,6	2,7	3,3	3,9	4,3	4,9
		kN.m/kg	19,5	19,5	19,5	19,5	19,5	19,5	19,5	19,5
COBB-60 maximum	EN ISO 535	g/m ²	40	40	40	40	-	-	-	-
COBB-1800 maximum	EN ISO 535	g/m ²	-	-	-	-	150	150	150	150
Production centre			SP FR	SP FR	UK	SP FR	SP FR	SP FR	SP	SP



Valid only for SAICA Paper Spain, Venizel and Partington



Valid only for SAICA EL



Valid only for SAICA Paper Spain, Venizel and Partington



100% Recycled and responsibly manufactured paper

The index guaranteed values refer to the nominal basis weight.

Valid from January 2019